



## TECHNICAL DATA

### POLYURETHANE ADHESION PROMOTER

<b>DESCRIPTION</b>	A one component, adhesion promoter for brush, roller or low pressure spray application.																		
<b>USES</b>	Polyurethane Adhesion Promoter is developed for use as an adhesion promoting primer for glass and concrete substrates and other siliceous surfaces, especially highly polished surfaces, prior to coating with Uroxsy's polymeric coatings.																		
<b>FEATURES</b>	A one pack system with low odour during installation and excellent adhesion to glass and cementitious substrates.																		
<b>COLOUR</b>	Clear																		
<b>SURFACE PREPARATION</b>	Substrates need to be clean, dry and dust free. Light etching with Uroxsy's CCA followed by thorough washing with clean water may be required to remove polishing residue from ground concrete. CCA prior to using this adhesion promoter improves adhesion to ceramic tiles and polymer modified concrete.																		
<b>APPLICATION</b>	Apply in an even coat at 10-20 m <sup>2</sup> , depending on substrate, per litre to wet the surface. Do not flood or puddle. Use mohair rollers, wide brush or low pressure spray.																		
<b>TECHNICAL DATA</b>	<table><tr><td>Composition:</td><td>Organo-Silane solution in alcohol</td></tr><tr><td>Film Thickness:</td><td>5 microns per coat DFT</td></tr><tr><td>Coverage Rate:</td><td>10-20 m<sup>2</sup> per litre</td></tr><tr><td>Touch Dry (Dust Free) :</td><td>Approximately 2 hours @ 20 °C</td></tr><tr><td>Topcoating:</td><td>Recoat within one day. Ensure good ventilation. Apply polyurethane after 4 hours minimum cure.</td></tr><tr><td>Special Note:</td><td>There must be enough time allowed to ensure that all the alcohol solvents, as well as the alcohol generated by the primer's cure mechanism, are fully evaporated. Alcohols, if present, can adversely affect the curing of polyurethanes.</td></tr><tr><td>Flashpoint:</td><td>12°C</td></tr><tr><td>Shelf Life:</td><td>6 months in unopened container</td></tr><tr><td>Clean Up:</td><td>Warm water with detergent</td></tr></table>	Composition:	Organo-Silane solution in alcohol	Film Thickness:	5 microns per coat DFT	Coverage Rate:	10-20 m <sup>2</sup> per litre	Touch Dry (Dust Free) :	Approximately 2 hours @ 20 °C	Topcoating:	Recoat within one day. Ensure good ventilation. Apply polyurethane after 4 hours minimum cure.	Special Note:	There must be enough time allowed to ensure that all the alcohol solvents, as well as the alcohol generated by the primer's cure mechanism, are fully evaporated. Alcohols, if present, can adversely affect the curing of polyurethanes.	Flashpoint:	12°C	Shelf Life:	6 months in unopened container	Clean Up:	Warm water with detergent
Composition:	Organo-Silane solution in alcohol																		
Film Thickness:	5 microns per coat DFT																		
Coverage Rate:	10-20 m <sup>2</sup> per litre																		
Touch Dry (Dust Free) :	Approximately 2 hours @ 20 °C																		
Topcoating:	Recoat within one day. Ensure good ventilation. Apply polyurethane after 4 hours minimum cure.																		
Special Note:	There must be enough time allowed to ensure that all the alcohol solvents, as well as the alcohol generated by the primer's cure mechanism, are fully evaporated. Alcohols, if present, can adversely affect the curing of polyurethanes.																		
Flashpoint:	12°C																		
Shelf Life:	6 months in unopened container																		
Clean Up:	Warm water with detergent																		
<b>SAFETY DATA</b>	If spraying wear a positive air-supplied full-face respirator. Avoid breathing the dust when sanding, use a dust mask. Wear protective clothing and safety glasses. Gloves are essential. Avoid contact with exposed skin. Before commencing work, apply barrier cream. Contains ethanol, absorption via skin and breathing fumes will raise blood alcohol level.																		

This information is, to the best of our knowledge, true and accurate, but any recommendations or suggestions which may be made are without guarantee, since the conditions of use are beyond our control. Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents covering any material or its use.

2K PROMOTER TD4 MAR14