



TECHNICAL DATA

REACTIVE PRIMER

POLYURETHANE PRIMER

DESCRIPTION	A one component, moisture cured polyurethane primer for brush, or roller application.
USES	Reactive primer has been developed for use as a high performance, clear, penetrating urethane primer to promote adhesion and to seal wooden and cementitious surfaces.
COLOUR	Clear/light amber
FEATURES	A moisture cured polyurethane with low free isocyanate monomer and excellent performance. Suitable for use as a primer for interior and exterior use.
SURFACE PREPARATION	Substrates should be clean, sound and thoroughly sanded to provide a keyed surface. Seek advice from Uroxsys Ltd for non-standard applications.
APPLICATION	Decant sufficient for immediate use into a roller tray or working pot. Seal original container to prevent moisture exposure. Decant only that sufficient for 30 minutes use and do not return unused product into the original container. Apply by floor brush or mohair roller. Apply following coats within 24 hours.
TECHNICAL DATA	Single component, moisture cured, aliphatic polyurethane primer. Film Thickness: Approximately 35 microns per coat DFT. Coverage Rate: 10-12m ² per litre per coat Final Cure: 7 days. Initial Cure: 24 hours at 20°C Shelf Life: 12 months in factory sealed containers. Number of coats: Use one coat of Reactive primer. Overcoat with a moisture curing build coat such as MCR Gloss or MCL Gloss within 24 hours. Clean Up: Use only Uroxsys Polyurethane Brush Cleaner.
SAFETY DATA:	Contains isocyanates. When sprayed, this product may be harmful by inhalation. Do not breathe vapour or spray. Avoid contact with skin and eyes. Wear suitable protective clothing, gloves, eye and face protection, including suitable breathing protection, such as an air-supplied respirator or hood. Avoid contact with exposed skin. Refer to MSDS sheet for further details.

DISCLAIMER: This information is, to the best of our knowledge, true and accurate, but any recommendations or suggestions which may be made are without guarantee, since the conditions of use are beyond our control. Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents covering any material or its use.

RP TD3 MAR14