



TECHNICAL DATA

STRONG REGLAZE SOLVENT

DESCRIPTION	A low-odour blend of strong solvents for recoating polyurethane floor finishes.
USES	To soften and sensitise an aged moisture-cured polyurethane floor surface to improve the adhesion of a recoat.
FEATURES	Low odour High flash point Effective on aged moisture-cured coatings Economical
SURFACE PREPARATION	Use after the floor has been thoroughly cleaned with Uroxsys Duracoat Floor Cleaner Concentrate, used at the label directed dilution plus 50% to remove waterbased contamination. Allow to dry. Sand floor with 100 grit to break the gloss. Detail dips and depressions by hand as required. Vacuum.
APPLICATION	Warning: Carry out a small trial in a non-critical area just to check that the old coating does not fry. Immediately prior to coating with Uroxsys Duracoat MCR, MCL or RHS, wipe over prepared floor with a clean lint free cloth saturated with Strong Reglaze Solvent to uniformly wet the area. Do not flood, or let run down into joins or cracks. Allow to evaporate then apply the coating, preferably within 30 minutes. On average, use approximately 1 litre for 30 – 40 m ² . Watch for signs of rejection whilst wiping on – this indicates contamination which must be removed.

TECHNICAL DATA

Application Rate:	Approximately 40m ² per litre
Working Time:	Apply coatings within 30 minutes of solvent evaporation.

SAFETY DATA: Wear gloves and protective clothing. Wear mask.

NOTE: A Material Safety Data Sheet is available on our website www.uroxsys.co.nz

This information is, to the best of our knowledge, true and accurate, but any recommendations or suggestions which may be made are without guarantee, since the conditions of use are beyond our control. Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents covering any material or its use.

TD2 0500